



Performance Features

- Stand-alone oil & water barrier
- Recyclable and Repulpable
- Excellent release properties
- Printable
- 30-Minute Cobb value of 10 or less
- Excellent Runability on Corrugators
- Slide Angle of 20 or greater
- FDA approve for food contact

Product Description

Ulterion® 531 OPV is a low viscosity coating developed for oil resistance & water resistance. It has applications in moisture barrier coatings, cold release coatings, food packaging coatings, and others where water & oil holdout is a requirement and process-curing conditions are minimal. **Ulterion® 531 OPV** provides the ultimate in water holdout. Its high surface tension allows it to be used as a base coat and coated over with a functional top coating as long as minimal cure is applied before secondary coating. This double bumped system can be used for optimizing water holdout and OGR and release properties.

Typical Properties

Appearance	Milky White
Solids, %	44
pH	7.0 - 8.5
Viscosity, cPs	60
Density	1.06
Origin	USA

Handling & Storage/Stability

The **Ulterion® 531 OPV** is a made to order product, which should be kept in Cool dry conditions. Storage temperatures above 90°F will decrease the shelf life considerably. Optimal storage conditions will yield a shelf life of 120 days from the date of manufacture.

The information contained herein is thought to be accurate in all aspects; however, the applications for these products mentioned are presented without guarantee or responsibility as to the suitability of our products whether used singly or in combination with other products. Nothing herein is to be taken as a license to operate under or as a recommendation to infringe any patents. The products are sold without warranty, expressed or implied, and are purchased at buyer's risk.

MARKET USES

- Sustainable container board packaging
 - Frozen Meats
 - Produce
 - Cooler Boxes
- Sustainable folding carton
 - Deli Boxes
 - Fast Food

Application Methods

The low viscosity of **Ulterion® 531 OPV** makes it particularly suitable for air knife and press applications where adequate drying capacity is available. Increased viscosity versions are also available as **Ulterion® 531 MV** and **Ulterion® 531 HV**.

FDA Status

Ulterion® 531 OPV may be used as in contact with all foods, except for foods or beverages containing alcohol, under all temperature conditions. **Ulterion® 531 OPV** complies fully with the Federal Food, Drug, and Cosmetic Act and all applicable food additive regulations, including 21 C.F.R. § 176.170 and 21 C.F.R. § 176.180, subject to the extractive limitations set out in Section 176.170(c).

Product Safety

When considering the use of **Ulterion®** brand products, please refer to the latest Safety Data Sheets (SDS). If a SDS for this product is required, please contact your **Jain Chem Representative**.